



**Nome**  
**/Name**

Pietra ricomposta  
*/Recomposed stone*

**Applicazione**  
**/Application**

Piani spessore 20 mm per Amorgòs DR, Lipsi P35-P48-P48SC, Svizzera Plus-Plana; Svizzera Plana Monolite  
*/20 mm tops for Amorgòs DR, Lipsi P35-P48-P48SC, Svizzera Plus and Plana; Svizzera Plana Monolite*

**Finitura**  
**/Finish**

Bordi levigati opachi (Thime, Vanilla, Anis, Ginger, Pepper) e lucidi (Cristobal, Base, Greige)  
*/Opaque (Thime, Vanilla, Anis, Ginger, Pepper) and glossy edges (Cristobal, Base, Greige)*

- La pietra ricomposta è l'innovativo materiale Tulli Zuccari utilizzato per i top propostoin 8 differenti finiture.
- Composta per il 93% da polveri di quarzo a diversa granulometria e per il 7% da resina strutturale poliestere, resiste alle aggressioni di acidi, all'abrasione, all'usura e ha elevate resistenze meccaniche.
- La pietra ricomposta ha pertanto qualità fisiche e prestazioni superiori al prodotto naturale di partenza, mantenendo le stesse caratteristiche estetiche. Il materiale è completamente anassorbente e resiste ad acidi e grassi.
- La pietra ricomposta di Tulli Zuccari presenta costanza di peso e spessore (19 mm); inoltre il disegno e la tonalità della superficie a vista è uniforme.
- La lastra in pietra può essere soggetta a svariate lavorazioni come il taglio, la bisellatura, la lucidatura. Le coste possono essere lavorate a 45°, come nel caso dei mobili Svizzera Plana MONOLITE.
- Per la pulizia si consigliano i normali prodotti detergenti per cucina e bagno. Il materiale comunque richiede una manutenzione poco impegnativa. Da evitare prodotti ad elevata basicità come la soda caustica, oppure detergenti a reazione acida per lo sporco resistente.
- *Recomposed stone is a new material used by Tulli Zuccari for the countertops and comes in 8 different finishes.*
- *Made 93% of quartz powder of different particle sizes and 7% of a structural polyester resin, this product is resistant to acids, abrasion and wear and it offers high mechanical resistance.*
- *The physical qualities and performance of the recomposed stone are better than those of the natural starting product while maintaining the same attractive look.*
- *Tulli Zuccari's recomposed stone has uniform weight, thickness, compactness, design and colour of the exposed surface.*
- *Recomposed stone can be machined, modelled and treated as such. Edge can be finished with 45° cut (Svizzera Plana MONOLITE).*
- *This material offers the advantage of less demanding maintenance procedures. This type of product can be cleaned either with detergents that have low basicity (avoid caustic soda) or with acid detergents for persistent grime.*